


## CLAIMS

1. A curable resin composition comprising:

- (I) a reactive silicon group-containing polyoxyalkylene  
 5 polymer wherein a introduction rate of a reactive silicon group  
 into a molecular terminus is not less than 85% as determined  
 by  $^1\text{H-NMR}$  analysis, and  
 (II) an epoxy resin.


10 2. The curable resin composition according to Claim 1  
 wherein the reactive silicon group-containing  
 polyoxyalkylene polymer (I) is obtainable by reacting (a) a  
 polyoxyalkylene polymer terminating in an unsaturated group of  
 either the general formula (1):



(1)

in the formula  $\text{R}^1$  represents a hydrocarbon group containing not  
 more than 10 carbon atoms;  $\text{R}^2$  represents a bivalent organic group  
 containing 1 to 20 carbon atoms which contains one or more members  
 selected from the group consisting of hydrogen, oxygen and  
 20 nitrogen as the constituent atom,


or the general formula (2):



(2)

in the formula  $\text{R}^1$  represents a hydrocarbon group containing not  
 more than 10 carbon atoms;  $\text{R}^2$  represents a bivalent organic group  
 25 containing 1 to 20 carbon atoms which contains one or more members  
 selected from the group consisting of hydrogen, oxygen and  
 nitrogen as the constituent atom,

with (b) a reactive silicon group-containing compound  
 of the general formula (3):



in the formula  $\text{R}^3$  and  $\text{R}^4$  each represents an alkyl group containing  
 1 to 20 carbon atoms, an aryl group containing 6 to 20 carbon  
 atoms, an aralkyl group containing 7 to 20 carbon atoms, or a  
 triorganosiloxy group of the formula  $(\text{R}')_3\text{SiO}-$ ; when two or more  
 35  $\text{R}^3$  or  $\text{R}^4$  groups are present, they may be the same or different;


R' represents a univalent hydrocarbon group of 1 to 20 carbon atoms; the three of R' groups may be the same or different; X represents a hydroxyl group or a hydrolyzable group; when two or more X groups are present, they may be the same or different;  
 5 a represents 0, 1, 2 or 3; b represents 0, 1 or 2; b may be the same or different over m repeats of  $-\text{Si}(\text{R}'_{2-b})(\text{X}_b)-\text{O}-$ ; m represents an integer of 0 through 19; provided, however, that the condition of  $a + \sum b \geq 1$  is satisfied,

(c) in the presence of a Group VIII transition metal catalyst.

10

3. The curable resin composition according to Claim 1 or 2

wherein a reactive silicon group-containing molecular chain terminus of the reactive silicon group-containing  
 15 polyoxyalkylene polymer (I) is represented by the following formula:



20

4. The curable resin composition according to Claim 1 to 3

comprising a compound having both a functional group capable of reacting with an epoxy group and a reactive silicon group

25

or a compound having both an epoxy group and a reactive silicon group.

SUB  
A2